




# INFUTAC Clear

## High strength molding spray adhesive



### DESCRIPTION

**INFUTAC is a spray adhesive specifically designed to hold reinforcing fibers in place.**

- Used for Infusion, vacuum moulding or RTM.
- Safely Fuses Laminating Materials to Structural Core Surfaces
- Provides Superior Holding During Forming Process
- Allows Resin to Obtain Maximum Tensile Sheer Strength
- Low Shrinkage in Curing
- Fine Mist Adhesive with green tracer for accuracy in application
- Fast Tack
- HAPS Free

**INFUTAC** is designed to hold fabrics (glass, agamid, carbon or peel ply), pads and similar types of dry materials to themselves or onto mold surfaces during resin infusion and RTM.

Most importantly, **INFUTAC** will not interfere with the curing process of vinyl esters, polyesters or epoxy\* resins. In fact, the adhesive is designed to ultimately become part of the polymer matrix. **INFUTAC** is a unique system to be used in the infusion process, and is designed specifically to overcome the problems normally associated with using other types of adhesives, such as bonding failure, resin blockage, surface defects in the finished product and so forth.

**INFUTAC** is designed to be used to give a provisional hold for fiberglass materials (cloth, mat, veil, fabric) in place prior to the application of fiberglass resin and/or gel coat to build up composites. It can also be used as a general purpose adhesive for a wide range of applications.

### PRODUCT USAGE

Adjust the spray flow: L (low) M (medium) and H (high). Make sure surface is clean, dry and free of grease, oil, dirt and other contamination. Spray an even coat of **INFUTAC** onto the surface. Do not wet the surface. Allow to dry and become slightly tacky. Apply fiberglass materials. Fiberglass material should hold in place. Infuse or inject the resin. Let the composite material cure (preferably overnight). Peel or shell of the composite from the mold. Recommended operating temperatures range from 15°C to 40°C.

### PROPERTIES

**Shelf life :** 18 Months

**Storage :** Not damaged by freezing. Return to room temperature prior to use.

**Flammability :** Flammable per industry standard flame projection test.

**Physical Properties :** Appearance : Green color or Clear

**Specific Gravity :** .70 to .74 grams/cc - (5.8 to 6.2 lbs/gal)

**Glue Solids :** 28% to 30%

**Solvent Base :** Hydrocarbon blend

**Packaging:** Aerosol 500ml (360g)

\*We recommend testing first since there are so many different epoxies: INFUTAC, is not an epoxy resin.

COMPLIES WITH  
THE CLP2015 REGULATION  
applicable since 1st June 15



	SPRAY
VOLUME	500ML
CANS	Consumable
NB/PALLET	1080

Indice D - Application date June 2015

