

**SCOTT BADER (PTY) LTD**  
**1 Lubex Road : Hammarsdale : KwaZulu-Natal : South Africa**  
**Tel : +27 (0)31 736 8500 Fax: +27 (0)31 736 8511**

**PROVISIONAL DATA SHEET FOR PRODUCT**

<b>PRODUCT NAME</b>	<b>Crystic 233 PA</b>
<b>PRODUCT TYPE</b>	Isophthalic laminating resin
<b>APPLICATION</b>	Hand lay up
<b>TYPICAL LIQUID PROPERTIES:</b>  Appearance Odour Viscosity (Brookfield LVT, 25°C, 100rpm, sp.3) Geltime at 25°C using 1phr Norox KP9 MEKP	Light pink Of styrene 350 cPS to 510 cPs 20 min to 30 minutes
<b>RECOMMENDATION FOR USE</b>	Base resin applications where an isophthalic resin is required
<b>KNOWN HAZARDS:</b>	1) Flammable: Flash point below 32°C 2) Harmful: Avoid skin and eye contact Avoid breathing vapour
<b>CAUTION NOTES:</b>	1) Flammable 2) Harmful
<b>SAFE HANDLING INFORMATION</b>	See separate Scott Bader Materials Safety Data Sheet
<b>STORAGE RECOMMENDATIONS</b>	Store in original containers below 25°C
<b>PACKAGING</b>	225kg drums, 25kg kegs

*All information is given in good faith but without warranty. We cannot accept responsibility for any damage, loss or patent infringement resulting from the use of this information.*