

Benchmark	PVC 60
NMG Europe	Atlas HPE 90

1) Finishing *grooves + holes 20 mm*

	PVC 60			HPE 90			SAVINGS	
Thickness	Core weight	Resin Weight	Infused Core Weight	Core weight	Resin Weight	Infused Core Weight	Resin	Weight
mm	g/m2	g/m2	g/m2	g/m2	g/m2	g/m2	g/m2	g/m2
10	600	1771	2371	950	888	1838	883	533
15	900	1852	2752	1425	943	2368	909	384
20	1200	1933	3133	1900	998	2898	935	235
25	1500	2014	3514	2375	1053	3428	961	86
30	1800	2095	3895	2850	1108	3958	987	-63
35	2100	2176	4276	3325	1163	4488	1013	-212
40	2400	2257	4657	3800	1218	5018	1038	-362

2) Finishing *scrim + deep grooving 30 mm*

	PVC 60			HPE 90			SAVINGS	
Thickness	Core weight	Resin Weight	Infused Core Weight	Core weight	Resin Weight	Infused Core Weight	Resin	Weight
mm	g/m2	g/m2	g/m2	g/m2	g/m2	g/m2	g/m2	g/m2
10	600	2196	2796	950	1132	2082	1064	714
15	900	2865	3765	1425	1589	3014	1276	751
20	1200	3534	4734	1900	2045	3945	1489	789
25	1500	4204	5704	2375	2502	4877	1701	826
30	1800	4873	6673	2850	2959	5809	1914	864
35	2100	5542	7642	3325	3416	6741	2126	901
40	2400	6211	8611	3800	3873	7673	2339	939